

Fan-to-sheet failure mode of FRP anchors

del Rey Castillo, E.¹, Kanitkar, R.², Smith S.³, Griffith, M.C.⁴, and Ingham, J.M.⁵

¹ Lecturer, Dept. of Civil and Environmental Engineering, University of Auckland, New Zealand.

² Principal KL Structures, San Francisco Bay Area, California USA

³ Professor, School of Environment, Science and Engineering, Southern Cross University, NSW, Australia

⁴ Professor, School of Civil, Environmental and Mining Engineering, The University of Adelaide, South Australia

⁵ Professor, Dept. of Civil and Environmental Engineering, University of Auckland, New Zealand.

Abstract

The use by practicing engineers of Fibre Reinforced Polymer (FRP) anchors in combination with Externally Bonded Reinforcements (EBR) is increasing. FRP anchors are typically used to prevent premature FRP-to-concrete debonding and/or to ensure the continuity of the load path from the FRP sheet into the concrete substrate. Recently proposed design models for most failure modes associated with FRP anchors, such as concrete cone failure and fibre rupture failure, are based on relatively large databases of test results, which ensures the validity of these models. This situation is not applicable for FRP-to-sheet failure, which is typically triggered by insufficient bond surface and has not received in-depth research attention to date.

The available data on the fan-to-sheet failure mode have been compiled together along with new data provided by the authors, with this data critically analysed in a quantitative and qualitative manner. Models pertaining to this failure mode are proposed, identifying strengths and shortcomings. The models are then used to statistically assess the available database and a final model is proposed, identifying areas in need of further research.

Keywords: FRP anchors, FRP strengthening, premature debonding, bond, anchorage, concrete, spike anchors

Corresponding author's email: edel146@aucklanduni.ac.nz

Introduction

Fibre Reinforced Polymer (FRP) anchors are bundles of fibres that, after being saturated with epoxy, in Externally Bonded Reinforcement (EBR) systems have one end introduced into the structure and the other end splayed out and bonded to the FRP sheet or plate. The part inside the structure is referred to as the anchor dowel, while the part outside is typically called the anchor fan or the anchor splay, as illustrated in Figure 1. FRP anchors are used to prevent or delay premature debonding of the FRP sheet and/or to ensure continuity of the load path from the sheet into the structure [1]. While other failure modes have been investigated to various levels of detail, and predictive models have been proposed [2]–[4], the fan-to-sheet failure mode illustrated in Figure 1 has received little research attention so far. A simple model based on the bond strength observed in a limited number of experimental tests was proposed [5], while two complex mechanics-based model were proposed for FRP-to-FRP connections, but the applicability for anchors is unknown [6]. The motivation of the research reported herein was to compile all the available research on fan-to-sheet failure, complement it with a few more datapoints generated by the authors, and verify whether either of the two previously developed models [5], [6] can be further improved.




Figure 1 FRP anchor exhibiting fan-to-sheet debonding failure mode

Experimental results

All datapoints used in this study are reported in Table 1 for single layer bond and in

Table 2 for double layer bond, i.e. with the anchor fan sandwiched between two FRP sheets. The data consists of details of the published reference, the specimen name, the area of the fan in cm^2 , the peak load (kN) at which fan-to-sheet debonding occurred, and the bond stress (MPa), defined as the peak load over the bond area. Kaniitkar [5] proposed to use a minimum bond strength of 35 percent of the bond shear strength of the resin, with a maximum value of 5 MPa if the bond shear strength of the resin is not available. This value is in general agreement with other recommendations [7]. The bond strength from almost all the studies reported in Table 1 and

Table 2 is below the 5.1 MPa baseline but, because those studies were not focused on fan-to-sheet debonding, the properties of the resin were not disclosed and the curing conditions are unknown, making it difficult to judge the reliability of these results.

Table 1 Data for single bond layer

| Ref | Specimen name | A_{bond} (cm ²) | Peak load (kN) | σ_{bond} (MPa) | Ref | Specimen name | A_{bond} (cm ²) | Peak load (kN) | σ_{bond} (MPa) |
|-----|---------------|--------------------------------------|----------------|------------------------------|-----|---------------|--------------------------------------|----------------|------------------------------|
| [8] | s15-2a000y-12 | 150 | 48.7 | 3.2 | ‡ | 7 | 126 | 73.3 | 5.8 |
| [8] | s15-2a150n-12 | 150 | 34.9 | 2.3 | ‡ | 8 | 126 | 85.1 | 6.8 |
| [8] | s15-2b150y-12 | 150 | 57.5 | 3.8 | ‡ | 9 | 126 | 76.3 | 6.1 |
| [8] | s15-2b150n-12 | 150 | 38.8 | 2.6 | ‡ | 10 | 126 | 73.1 | 5.8 |
| [8] | s15-2c150n-12 | 150 | 48.4 | 3.2 | ‡ | 11 | 126 | 89.5 | 7.1 |
| [8] | s15-2A150h-10 | 150 | 46.7 | 3.1 | ‡ | 12 | 126 | 98.3 | 7.8 |
| [8] | s20-2b150h-15 | 200 | 58.6 | 2.9 | ‡ | 13 | 126 | 83.2 | 6.6 |
| [9] | s1-100-2 | 14 | 3.0 | 2.1 | ‡ | 14 | 126 | 69.3 | 5.5 |
| [9] | s2-200-2 | 14 | 4.0 | 2.8 | ‡ | 15 | 126 | 81.9 | 6.5 |
| [5] | S1 | 65 | 54.0 | 8.3 | ‡ | 16 | 126 | 97.0 | 7.7 |
| [5] | S2 | 65 | 60.7 | 9.3 | ‡ | 17 | 126 | 86.9 | 6.9 |
| [5] | S3 | 65 | 69.8 | 10.7 | ‡ | 18 | 168 | 112.6 | 6.7 |
| [5] | S4 | 65 | 64.1 | 9.9 | ‡ | 19 | 168 | 102.5 | 6.1 |
| [5] | S5 | 65 | 69.1 | 10.6 | ‡ | 20 | 168 | 122.6 | 7.3 |
| [5] | S6 | 65 | 73.1 | 11.2 | ‡ | 21 | 168 | 119.3 | 7.1 |
| † | n1a-200 | 200 | 53.9 | 2.7 | ‡ | 22 | 168 | 129.4 | 7.7 |
| † | n1b-300 | 450 | 70.5 | 1.6 | ‡ | 23 | 207 | 119.1 | 5.8 |
| † | n1c-250 | 313 | 23.6 | 0.8 | ‡ | 24 | 207 | 120.1 | 5.8 |
| † | n1d-250 | 313 | 67.1 | 2.1 | ‡ | 25 | 207 | 139.0 | 6.7 |
| † | n1e-275 | 111 | 30.4 | 2.7 | ‡ | 26 | 207 | 126.5 | 6.1 |
| † | n1f-205 | 156 | 38.5 | 2.5 | | | | | |

† New data points from del Rey Castillo, and ‡ New data points from Kanitkar

Table 2 Data for double bond layer

| Ref | Specimen name | A_{bond} (cm ²) | Peak load (kN) | σ_{bond} (MPa) | Ref | Specimen name | A_{bond} (cm ²) | Peak load (kN) | σ_{bond} (MPa) |
|------|---------------|--------------------------------------|----------------|------------------------------|-----|---------------|--------------------------------------|----------------|------------------------------|
| [10] | N5H1.4Mc | 24 | 64.1 | 26.6 | † | n2f-350 | 1225 | 58.0 | 0.5 |
| [10] | B5L1.4Md | 24 | 40.5 | 16.8 | † | n2g-350 | 1225 | 114.5 | 0.9 |
| [10] | B5H1Md | 24 | 67.6 | 28.1 | † | n2h-240 | 360 | 33.8 | 0.9 |
| [11] | R-1 | 130 | 54.3 | 4.2 | † | n2i-240 | 360 | 31.0 | 0.9 |
| [11] | R-2 | 130 | 55.4 | 4.3 | † | n2j-350 | 1225 | 180.2 | 1.5 |
| [11] | R-3 | 130 | 48.9 | 3.8 | † | n2k-250 | 170 | 105.0 | 6.2 |
| [11] | R-4 | 130 | 48.0 | 3.7 | † | n2l-300 | 900 | 164.5 | 1.8 |
| † | n2a-150 | 113 | 63.1 | 5.6 | ‡ | 27 | 207 | 145.1 | 7.0 |
| † | n2b-300 | 450 | 150.6 | 3.3 | ‡ | 28 | 207 | 145.5 | 7.0 |
| † | n2c-200 | 400 | 61.7 | 1.5 | ‡ | 29 | 207 | 147.2 | 7.1 |
| † | n2d-200 | 400 | 51.1 | 1.3 | ‡ | 30 | 207 | 148.0 | 7.2 |
| † | n2e-250 | 625 | 63.5 | 1.0 | ‡ | 31 | 207 | 146.7 | 7.1 |

† New data points from del Rey Castillo, and ‡ New data points from Kanitkar

Design model

Revised Kanitkar model

The model proposed by Kanitkar was based on the shear strength of a resin with a tensile strength of 55 MPa, but the resin strength in the del Rey Castillo data was 25 MPa as obtained from tests done in accordance with the pertinent ASTM standard [12]. If a ratio of the resin tensile strength is used instead of a ratio of shear strength, the result is 10.8% and 12.2% for del Rey and Kanitkar respectively. Therefore, a suggestion is made to use 10% of the tensile strength as bond strength if the bond shear strength is not available, resulting in equation (1). It is important to note that this model does not consider anchor shape or dimensions.

$$V_{sb} = 0.35\tau_r A_{fan} \quad (1a)$$

If τ_r is not available,

$$V_{sb} = \max \begin{cases} 5A_{fan} \\ 0.1\sigma_r A_{fan} \end{cases} \quad (1b)$$

Where:

- V_{sb} = fan-to-sheet failure load [kN]
- τ_r = bond shear strength of the resin [MPa]
- σ_r = tensile strength of the resin [MPa]
- A_{fan} = area of the fan [mm²]

Revised Singh model

Singh et al. developed two models, but only the simplified model is used for simplicity. First the critical bond length needs to be calculated using equation (2) for single lap bonded anchor fans and equation (3) is used for double lap bonded anchor fans (i.e. anchor fan sandwiched between two FRP sheets). Once the critical bond length is known the fan-to-sheet failure load can be calculated with equation 4 for single lap bonded anchor fans and with equation 5 for double lap bonded anchor fans.

$$L_{cr}^{sg} = \frac{3\sigma_f t_f}{2\sigma_r} \quad (2)$$

$$L_{cr}^{db} = \frac{2\sigma_f t_f}{\sigma_r} \quad (3)$$

$$V_{sb}^{sg} = \begin{cases} 0.4\sigma_r b_f L & L < L_{cr} \\ 0.6\sigma_f b_f L & L \geq L_{cr} \end{cases} \quad (4)$$

$$V_{sb}^{db} = \begin{cases} 0.6\sigma_r b_f L & L < L_{cr} \\ 1.2\sigma_f b_f L & L \geq L_{cr} \end{cases} \quad (5)$$

Where:

- L_{cr}^{sg} = is the critical bond length of singly bonded fans [mm]
- L_{cr}^{db} = is the critical bond length of doubly bonded fans [mm]
- σ_f = tensile strength of the FRP [MPa]

- t_f = thickness of FRP [mm]
 σ_r = tensile strength of the resin [MPa]
 V_{sb}^{sg} = fan-to-sheet failure load for singly bonded fans [kN]
 V_{sb}^{db} = fan-to-sheet failure load for doubly bonded fans [kN]
 b_f = width of the anchor fan [mm]
 L = length of the anchor fan [mm]

Because the resin properties were not reported in the literature, only the data from the authors could be used to assess how the revised Singh model predicts the failure load observed in the experiments. The load calculated using the above revised Singh model is 0.8 times the experimental value for single lap bonded anchor fans using Kanitkar's data and is 2.7 times the experimental value using the del Rey Castillo data. The discrepancy is even more significant for double lap bonded anchor fans, with the ratio between predicted and experimental values being 1.1 for the Kanitkar's data and 4.6 for the del Rey Castillo's data. The use of this model is therefore not recommended for anchors, as the model cannot reliably predict the fan-to-sheet failure load.

Conclusions

Two methods to calculate the fan-to-sheet failure load are proposed, one based on a percentage of the tensile or the shear strength of the resin and a second one using a complex model based on fracture mechanics. The revised Kanitkar model described in Equations 1a and 1b can be safely used to calculate the fan-to-sheet failure load but does not consider anchor geometry. The revised Singh model does not accurately predict the data, and therefore is not recommended for anchors until further research is done.

References

- [1] E. del Rey Castillo, D. Dizhur, M. C. Griffith, and J. M. Ingham, "Strengthening RC structures using FRP spike anchors in combination with EBR systems," *Compos. Struct.*, vol. 209, pp. 668–685, 2019.
- [2] S. J. Kim and S. T. Smith, "Pullout Strength Models for FRP Anchors in Uncracked Concrete," *J. Compos. Constr.*, vol. 14, no. 4, pp. 406–414, 2010.
- [3] E. del Rey Castillo, M. C. Griffith, and J. M. Ingham, "Straight FRP anchors exhibiting fiber rupture failure mode," *Compos. Struct.*, vol. 207, pp. 612–624, 2019.
- [4] E. del Rey Castillo, M. C. Griffith, and J. M. Ingham, "Experimental testing and design model for bent FRP anchors exhibiting fiber rupture failure mode," *Compos. Struct.*, vol. 210, pp. 618–627, 2019.
- [5] R. Kanitkar, S. T. Smith, and C. Lewis, "An Experimental Investigation on the splay portion of embedded FRP tension anchors," in *Proceedings of The 8th International Conference on Fibre-Reinforced Polymer (FRP) Composites in Civil Engineering (CICE 2016)*, 2016, pp. 413–418.
- [6] A. Singh, E. del Rey Castillo, and J. M. Ingham, "FRP-to-FRP bond characterization and force-based bond length model," *Compos. Struct.*, vol. 210, pp. 724–734, 2019.
- [7] J. O. Jirsa, W. M. Ghannoum, C. H. Kim, W. Sun, W. Shekarchi, N. Alotaibi, D. Pudleiner, J. Zhu, S. Lu, and H. Wang, *Use of Carbon Fiber Reinforced Polymer (CFRP) with CFRP Anchors for Shear-Strengthening and Design Recommendations/Quality Control Procedures for CFRP Anchors*. Austin, Texas, USA: Technical Report No. FHWA/TX-16/0-6783-1. Center for Transportation

- Research, The University of Texas at Austin, 2017.
- [8] K. Kobayashi, S. Fujii, Y. Yabe, H. Tsukagoshi, and T. Sugiyama, "Advanced wrapping system with CF anchor - Stress transfer mechanism of CF anchor," in *Proceedings of the Fifth International Conference on Fiber Reinforced Polymer for Reinforced Concrete Structures (FRPRCS-5)*, 2001.
- [9] S. T. Smith and S. J. Kim, "Shear strength and behaviour of FRP spike anchors in FRP-to-concrete joint assemblies," in *Proceedings of the Fifth International Conference on Advanced Composite Materials in Bridges and Structures (ACMBS 5)*, 2008.
- [10] W. Sun, *Behavior of Carbon Fiber Reinforced Polymer (CFRP) Anchors Strengthening Reinforced Concrete Structures*. Doctor of Philosophy Thesis at The University of Texas at Austin, Department of Civil Engineering, 2014.
- [11] P. Villanueva Llauradó, J. Fernández Gómez, and F. J. González Ramos, "Influence of the Anchor Fan Position on the Performance of FRP Anchors," *High Tech Concr. Where Technol. Eng. Meet*, vol. Springer, pp. 191–198, 2018.
- [12] ASTM D638, *Standard Test Method for Tensile Properties of Plastics*. West Conshohocken, Pennsylvania: American Society for Testing and Materials (ASTM), 2014.